

**Elevator Cab Cladding**

Z-2002-031

Zodiaq® Quartz Surfaces can be used as a cladding material for elevator cabs. The mechanical properties of Zodiaq® Quartz Surfaces are equal, or superior, to natural stone products.

Please refer to the Zodiaq® Internal Wall Cladding Specification for techniques that are acceptable for anchoring Zodiaq® tiles or panels to an elevator cab. Floor tile can be adhered using traditional tile setting and grouting techniques.

*Note: DuPont does not provide a warranty for installation of Zodiaq® in commercial applications.*

Relevant physical properties and product data that may be required by code bodies are provided below:

Property	Typical Result	Procedure
Flexural Strength	>5300 psi	ASTM D 790
Flexural Modulus	5.3 – 5.7 E6 psi	ASTM D 790
Flexural Elongation	>0.1 %	ASTM D 790
Colorfastness	Passes	ANSI Z124.6.5.1
Stain Resistance	Passes	ANSI Z124.6.5.2
Wear and Cleanability	Passes	ANSI Z124.6.5.3
Cigarette Resistance	Passes	ANSI Z124.6.5.4
Chemical Resistance	Passes	ANSI Z124.6.5.5
Flammability	Class I and Class A	ASTM E 84
Flame Spread	FSI = 0 for 3 cm and 5 for 2 cm	& NFPA 255
Smoke Developed	SDI= 40 for 3 cm and 75 for 2 cm	
Chemical	Passes	ANSI Z124.6.5.5
Nominal Thickness	2 and 3 cm	

Please refer to the Zodiaq® Spec Data Sheet for additional physical properties of Zodiaq® Quartz Surfaces.

The information contained in this Technical Bulletin is given by the E. I. du Pont de Nemours and Company free of charge. It is based on technical data which DuPont believes to be reliable and is intended for use by persons having knowledge of this technical area at their own discretion and risk. Seller assumes no responsibility for results obtained or damage incurred from the use of this Technical Bulletin either in whole or in part by a buyer of Zodiaq®.

Zodiaq® is a DuPont registered trademark for its quartz surfaces.  
 Copyright 2001 E. I. du Pont de Nemours and Company. Printed in the U.S.A